

DATA SHEET

/ ECOKRAFT BAGS

PAPER QUALITY EB

TECHNICAL CHARACTERISTICS

UNE / EN / ISO - 536	GRAMMAGE	g/m ²	60	70	75	80	85	90	100	110	115	120	125	200	
UNE / EN / ISO- 287	Moisture	%	8,0	8,0	8,0	8,0	8,0	8,0	8,0	8,0	8,0	8,0	8,0	8,0	+/- 1,5
UNE / EN / ISO - 1924 / 2	Stretch MD	%	2,0	2,0	2,0	2,0	2,0	2,0	2,0	2,0	2,0	2,0	2,0	2,0	-10%
UNE / EN / ISO - 1924 / 2	Stretch CD	%	5,5	6,0	6,0	6,0	6,0	6,0	6,0	6,0	6,0	6,0	6,0	6,0	-10%
UNE / EN / ISO - 1924 / 2	Lenght strength MD	m	6.500	8.700	8.700	8.700	8.700	8.700	8.700	8.700	8.700	8.700	8.700	8.700	-10%
UNE / EN / ISO - 1924 / 2	Lenght strength CD	m	3.000	3.200	3.200	3.200	3.200	3.200	3.200	3.200	3.200	3.200	3.200	3.200	-10%
UNE / EN / ISO - 1924 / 2	Tensile Index MD	Nm/g	64	85	85	85	85	85	85	85	85	85	85	85	-10%
UNE / EN / ISO - 1924 / 2	Tensile Index CD	Nm/g	29	31	31	31	31	31	31	31	31	31	31	31	-10%
UNE / EN / ISO – 535	Cobb 60 T	g/m ²	30	30	30	30	30	30	30	30	30	30	30	30	MAX. 40
UNE / EN / ISO – 535	Cobb 60 B	g/m ²	30	30	30	30	30	30	30	30	30	30	30	30	MAX. 40
EN / ISO – 2758	Burst Index	kPa m ² /g	3,2	3,8	3,8	3,8	3,8	3,8	3,8	3,8	3,8	3,8	3,8	3,6	Indicative
UNE / ISO 5636-5	Gurley (air resistance)	S	40	50	50	55	55	60	65	70	70	75	80	90	Indicative



UNE / EN / ISO - 20187

SAMPLE CONDITIONING

Relative humidity

50 +/- 2 %

Temperature

23 +/- 1°C

MD: Machine Direction

CD: Cross Direction

T: Top

B: Bottom

OBSERVATIONS: For the other grammages of the nominals ones indicated in the table, values of the grammages immediately below shall be applied
Grammage tolerance ± 4% to 100 g/m², ± 3% to 200 g/m²

SEDE CENTRAL

Avenida Diagonal 403 6to.3
08008 Barcelona
T. +34 933 042 860
alier@aliersa.com

FÁBRICA DE PAPEL

Km. 10 de la carretera N-230
de Lleida al Valle de Arán
25124 Rosselló (Lleida)
T. +34 973 732 705
alierlle@aliersa.com